



Cloud 9 Flame Retardant 6

Cloud 9 Combustion Modified Core

Suitable for Heavy Contract Use

For Use in Doublestick and Stretch-Fit Applications

Conforms to EC Marine Directives

CLOUD



RANGE OF UNDERLAYS

PURE LUXURY UNDER THE CARPET

Top Surface	Printed Corona Treated Polymer Film	
Bottom Surface	Corona Treated Polymer Film	
Nominal Thickness	6.00 mm	
Nominal Roll Weight	15.3 Kg	33.7 lb
Weight Per Unit Area	1015 g/m ²	30 oz/yd ²
Roll Length	11.0 m	36.0 ft
Roll Width	1.37 m	54 in
Guarantee	Lifetime of the Carpet (When used in recommended areas)	

Recommended Areas of Use

Heavy contract and domestic use areas. Large areas where a flat firm fitting is required.

BS. 5808 : 1991 Test Results - British Standard for Carpet Underlays

End Use Classification	BS. 5808	HC/U
Work of Compression after 1000 impacts	BS. 4098	>90 J/m ²
Retention of Work of Compression	BS. 4098	>90 %
Loss in Thickness after Static Loading	BS. 4939	<5.00 %
Loss in Thickness after Dynamic Loading	BS. 4052	<5.00 %
Resistance to Cracking	BS. 5808 (A)	Pass

Other Relevant Tests

Thermal Resistance (TOG Rating)	BS. 4745	1.4 TOG
Impact Sound Improvement Index		
(Test / Rated to BS EN ISO 140 - 8 / BS EN ISO 717-2)	30 dB	
International Marine Flammability Test	IMO 653	Pass
IMO - Marine Smoke & Toxicity Test	MSC 61 (67)	Pass
Hot Metal Nut Test	BS. 4790	Pass - Low radius of effect
French Epiradiateur	NFP 92-501	Pass Class M3
European Type Approval Certificate		
Conforms to European Marine Equipment Directive (MED) 96/98/EC		

Flame Retardant 6

Disclaimer

Whilst every effort is made to ensure its accuracy, the data on this sheet is meant for information purposes only. The typical properties listed are the result of extensive laboratory tests, but since Ball and Young has no control over the end use of each material, we cannot guarantee these results are obtained in practice. Users should conduct their own tests to determine the suitability of each material to its intended application.

